

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1 300 653 366
Fax: 1300 893 171

Internet: www.awqc.com.au
Email: awqc@sawater.com.au



FINAL REPORT


This report supersedes the following issued reports:
77922.

Report Information

Report ID : 85026
Submitting Organisation : 00109275 : RAMSET FASTENERS (AUST) PTY LTD
Account : 130255 : RAMSET FASTENERS (AUST) PTY LTD
AWQC Reference : 130255-2010-CSR-1 : Chemset TM 801
Project Reference : PT-1368
Product Designation : Chemset TM 801
Composition of Product : Vinyl Ester Polymer
Product Manufacturer : Not applicable.
Use of Product : In-Line/Anchoring Adhesive
Sample Selection: As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020:2005 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2005
Extracts : Extracts were prepared as described in Appendix C, D, E, F, G, H.
Project Completion Date : 07-Dec-2010
Project Comment : The results presented herein demonstrate compliance of Chemset TM 801 to AS/NZS 4020 when exposed at area to volume ratios up to 2500 mm²/L at 20°C ± 2°C.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1300 653 366
Fax: 1300 893 171

Internet: www.awqc.com.au
Email: awqc@sawater.com.au



FINAL REPORT

This report supersedes the following issued reports:
77922.

Summary of Results

APPENDIX	RESULTS
C – Taste of Water Extract	Passed at an exposure of 2500 mm2 per Litre.
D – Appearance of Water Extract	Passed at an exposure of 2500 mm2 per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 2500 mm2 per Litre.
F – Cytotoxic Activity of Water Extract	Passed at an exposure of 2500 mm2 per Litre.
G – Mutagenic Activity of Water Extract	Passed at an exposure of 2500 mm2 per Litre.
H – Extraction of Metals	Passed at an exposure of 2500 mm2 per Litre.

Summary Comment : Not applicable.



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

PO Box 1751
Adelaide SA 5001

250 Victoria Square
Adelaide SA 5000

Tel: 1 300 653 366
Fax: 1300 883 171

Internet: www.awqc.com.au
Email: awqc@sawater.com.au




FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.2 Taste of Water Extract

Sample Description	The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm ² per Litre. Extracts were prepared using 1600 mL volumes of 50 mg/L hardness water.
Extraction Temperature	20°C ± 2°C.
Test Method	Taste of Water Extract (Appendix C)
Test Information	
Scaling Factor	Not applied.
Results	Not detected.
Evaluation	The product passed the requirements of clause 6.2 when tested at an exposure of 2500 mm ² per litre.
Number of Samples	2.
Test Comment	Not applicable.



Peter Christopoulos
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.3 Appearance of Water Extract

Sample Description The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1600 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Appearance of Water Extract (Appendix D)

Scaling Factor Not applied.


Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	<0.1	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 2500 mm² per litre.

Number of Samples 1.

Test Comment Not applicable.



Joanne Clark
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applied.

Results

Mean Dissolved Oxygen	Control	7.2 mg/L
Mean Dissolved Oxygen Difference	Positive Reference	5.8 mg/L
	Negative Reference	<0.1 mg/L
	Test	0.90 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 2500 mm² per litre.

Number of Samples 1.

Test Comment Not applicable.



Stephanie Semczuk
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.5 Cytotoxic Activity of Water Extract

Sample Description

The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1600 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Cytotoxic Activity of Water Extract (Appendix F)

Scaling Factor Not applied.

Results Non-cytotoxic.

Evaluation The product passed the requirements of clause 6.5 when tested at an exposure of 2500 mm² per litre

Number of Samples 1.

Test Comment The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Brendon King
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.6 Mutagenic Activity of Water Extract

Sample Description The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1600 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Mutagenic Activity of Water Extract (Appendix G)

Scaling Factor Not applied.

Results

<u>Bacteria Strain</u>	<u>Number of Revertants per Plate</u>				
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	40, 24, 40	44, 50, 42	1939, 2118, 2244	<u>NPD</u> (20µg)
Mean ± Standard deviation		34.7 ± 9.2	45.3 ± 4.2	2100.3 ± 153.3	
	+	53, 28, 36	54, 45, 49	1635, 1591, 1776	<u>2-AF</u> (20µg)
Mean ± Standard deviation		39.0 ± 12.8	49.3 ± 4.5	1667.3 ± 96.6	
<i>Salmonella typhimurium</i> TA100	-	224, 222, 197	196, 189, 182	829, 718, 752	<u>Azide</u> (1.0µg)
Mean ± Standard deviation		214.3 ± 15.0	189.0 ± 7.0	766.3 ± 56.9	
	+	156, 144, 146	149, 144, 135	921, 1107, 1026	<u>2-AF</u> (20µg)
Mean ± Standard deviation		148.7 ± 6.4	142.7 ± 7.1	1018.0 ± 93.3	
<i>Salmonella typhimurium</i> TA102	-	594, 534, 600	570, 549, 481	1525, 1495, 1558	<u>Mitomycin C</u> (2µg)
Mean ± Standard deviation		576.0 ± 36.5	533.3 ± 46.5	1526.0 ± 31.5	
	+	392, 382, 388	370, 423, 438		
Mean ± Standard deviation		387.3 ± 5.0	410.3 ± 35.7		

Comments S9 was used as a metabolic activator. NPD (4-nitro-o-phenylenediamine), Azide, and Mitomycin C are specific positive controls for strains TA98, TA100 and TA102 respectively while 2 - AF (2-aminofluorene) when used in conjunction with S9 is a positive control for both TA98 and TA100

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 2500 mm² per litre

Number of Samples 1.

Test Comment Not applicable.



Peter Christopoulos
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

This report supersedes the following issued reports:
77922.

CLAUSE 6.7 Extraction of Metals

Sample Description The sample consisted of a single strip with dimensions 10 mm x 140 mm with a 4 mm thickness providing a total surface area of approximately 2500 mm² per Litre. Extracts were prepared using 1600 mL volumes of 50 mg/L hardness water.

Extraction Temperature 20°C ± 2°C.

Test Method Extraction of Metals (Appendix H)

Scaling Factor Not applied.

Method of Analysis All methods used to determine concentrations of metals are based on those described in the 21st edition of Standard Methods for the Examination of Water and Wastewater published by the APHA, AWWA and WEF (2005). The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre. Concentration of the metals described in Table 2 of the AS/NZS 4020:2005 are determined as follows:
Antimony, Arsenic, Barium, Cadmium, Chromium, Copper, Lead, Mercury, Molybdenum, Nickel and Selenium by inductively coupled plasma mass spectrometry.
Silver by graphite furnace absorption spectrophotometry (Varian).

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.007
Barium	0.0005	<0.0005	<0.0005	<0.0005	0.7
Cadmium	0.0001	<0.0001	<0.0001	<0.0001	0.002
Chromium	0.0001	<0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	0.0001	<0.0001	0.0001	2.0
Lead	0.0001	<0.0001	<0.0001	<0.0001	0.01
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	<0.0001	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.002	<0.00003	<0.00003	<0.00003	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 2500 mm² per litre

Number of Samples 1.

Test Comment Not applicable.



Dzung Bui
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
This document is issued in accordance
with NATA's accreditation requirements.
Accredited for compliance with ISO/IEC 17025